



600 Guy Paine Road
 Macon, Ga
 31206
 USA
 Tel. (478) 781.9488

SD-STANDARD-100™

Product Characteristics

Product Description

SD-Standard-100™ family of polypropylene based compounds covers broad range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate. Custom grades are available with features such as high impact, heat stabilizers and UV stabilizers.

General Information

Features	<ul style="list-style-type: none"> Alloy 	<ul style="list-style-type: none"> General Purpose
Applications	<ul style="list-style-type: none"> Asphalt modification Construction Industrial 	<ul style="list-style-type: none"> Consumer goods Automotive
Processing Method	<ul style="list-style-type: none"> Injection Molding 	<ul style="list-style-type: none"> Extrusion
Filler	<ul style="list-style-type: none"> 15%-20% Filler by Weight 	
Form	<ul style="list-style-type: none"> Pellets 	
Appearance	<ul style="list-style-type: none"> Black, Gray 	

Technical Information

Physical Properties	Measured Value	Standards
Specific Gravity	<ul style="list-style-type: none"> 1.02 	<ul style="list-style-type: none"> ASTM D792
Specific Volume	<ul style="list-style-type: none"> 0.96 cm³/gr 	<ul style="list-style-type: none"> ASTM D792
Melt Index (230°C/2.16kg)	<ul style="list-style-type: none"> 18-23 g/10min. 	<ul style="list-style-type: none"> ASTM D1238
Mechanical Properties	Measured Value	Standards
Tensile Stress, at break	<ul style="list-style-type: none"> 25 MPa 	<ul style="list-style-type: none"> ASTM D638
Tensile Stress, at yield	<ul style="list-style-type: none"> 17 MPa 	<ul style="list-style-type: none"> ASTM D638
Tensile Strain, at break	<ul style="list-style-type: none"> 113% 	<ul style="list-style-type: none"> ASTM D638
Notched Izod Impact	<ul style="list-style-type: none"> 0.98 ft.lbs/in. 	<ul style="list-style-type: none"> ASTM D256
Hardness (Shore D)	<ul style="list-style-type: none"> 67 	<ul style="list-style-type: none"> ASTM D2240

NOTICE: ALL STATEMENTS, INFORMATION AND DATA GIVEN HEREIN ARE RELIABLE BUT ARE PRESENTED WITHOUT GUARANTY, WARRANTY, OR RESPONSIBILITY OF ANY KIND, EXPRESSED OR IMPLIED. STATEMENTS OR SUGGESTIONS CONCERNING POSSIBLE USE OF OUR PRODUCTS ARE MADE WITHOUT REPRESENTATION OR WARRANTY THAT ANY SUCH USE IS FREE OR PATENT INFRINGEMENT, AND ARE NOT RECOMMENDATIONS TO INFRINGE ANY PATENT. THE USER SHOULD NOT ASSUME THAT ALL SAFETY MEASURES ARE INDICATED, OR THAT OTHER MEASURES MAY NOT BE REQUIRED.